

DESCRIPTION

PL031 is an Oil Tolerant High Strength Retainer, designed for direct use on as received parts such as those with oily films.

Typical Properties (Liquid Product)	
Chemical base:	Modified Methacrylate
Colour:	Green
Viscosity:	110-140cps
Specific Gravity	1.08
Max. gap filling:	0.1mm
Temp Range:	-50°C to 150°C
Physical Properties (cured product) @23°C	
Measured on M10 x 20 bolt, loose free running.	
Initial strength:	1 hour
Final strength:	24 hours
Cured Performance	
Full Cure Time:	24 hours
Static Shear (degreased)	28 N/mm ² typical
Statics Shear (oiled film)	21-24 N/mm(2) (ISO/MIL)
The test methods used are ISO 10123/MIL 46082B on mild steel Pin/Collars to the above specifications.	

APPLICATIONS

PL031 Retainer has been designed for the permanent retention of close fitting parts. It is a high strength, low viscosity securing compound, used for the retaining of cylindrical parts in situ with the ability to overcome light oil residues or contamination during assembly. PL031 is ideal for slip fit or interference fits on gears, pulleys, keyways, splines, sleeves and bushes etc.

Use as a conventional high strength Retainer on cleaned parts with strengths up to 28 N/mm² or as a convenient all-purpose locker on oily parts, with >20N/mm² strength depending on oil type and film

DIRECTIONS FOR USE

Where possible, remove thick deposits of grease or dirt. However, PL031 will penetrate the film once it has been tightened.

- Parts should be clean, dry and dust free.
- Degreased parts will assist results.
- Apply sufficient product to fill joint.
- Assemble parts in traditional manner.
- To achieve handling strength allow product to solidify (approximately 15 minutes).

[cont...]

ZYLOCK[®] The information contained herein is produced in good faith and is believed to be reliable but is for guidance only. Zylock[®] and its agents cannot assume liability or responsibility for results obtained in the use of its products by persons whose methods are outside or beyond our control. It is the users responsibility to determine the suitability of any of the products and methods of use or preparation prior to use mentioned in our literature and furthermore the users responsibility to observe and adopt such precautions as may be advisable for the protection of personnel and property in the handling and use of any of our products.

COMPATIBLE ACTIVATORS , ACCELERATORS & PRIMERS

Activators such as A471 Structural Activator or the faster A649 Structural Activator can be used, however, up to 30% strength loss can occur when using accelerators

PACKAGING

Bottles: 10ml, 50ml & 250ml

Bulk: 15kg

STORAGE & SHELF LIFE

Store in a cool area out of direct sunlight

Shelf Life: 12 months @ 20°C

HEALTH & SAFETY

Please refer to SDS